

Using Sheep Coats to Control Vegetable Matter Contamination

Produced for the CRC for Premium Quality Wool undergraduate program by;

Dr. Brad Crook, The University of New England.



CRC

for

Premium

Quality

Wool

Rugged (R) vs unrugged (U) sheep: VM% and VM residuals in wool top

	Location		VM%	VM particles per 100g top
	Birchip, Vic	R U	0.4 0.9	4 2
1	Wanbi, SA	R U	4.1 4.7	90 160
3	Sandalwood, SA	R U	4.4 9.7	16 45
	Deniliquin, NSW	R U	0.7 2.5	6 20

Brad Crook Source: Abbott (1979)